

Glass fiber putty FBR-GLASS

(art. 134-1000, 134-1800)

Description:

Polyester glass fiber putty «FBR-Glass» for alignment and strengthening of surfaces at body repair vehicles. Compatible for any steel (ferrous and galvanized metal, aluminum) and plastic elements (plastic, carbon fiber, fiberglass). High mechanical resistance and good elasticity.

Properties putty:

- High hardness.
- High elasticity.
- Very soft and easy treatment.
- Perfect repair of large defects.
- Excellent adhesion.

Technical data:

VOC content: 2004/42/II(b)(250) 250









Putty FBR-GLASS:

Shelf life: 24 months Density: 1,8 g/cm³ Color: green

Hardener:

Shelf life: 18months Density: 1,2 g/cm³ Color: pink

Application:

	Sanding with P80-P240
	Cleaned, dried, degreased and sanded
	Mixing putty (A) and hardener (B) in a ratio 50:1. Hardener included
	Pot life - up to 3-6 min. (at 20°C)
	Apply with scraper. Film thickness 2-3 mm
	Drying time 15-20 min. (at +20°C)
	Infrared drying 5 min. (at +60°C)
	Sand dry with first P80-P180, than P180-P240